



3M™ Membrana™ OXPAN™ Capillary Membrane, Type PP 50/280

Chemical Composition	
Polymer	Polypropylene
Solvent residues	≤ 100 ppm

Physical properties	
Wall thickness	50 ± 10 µm
Outer diameter	380 +20/-15 µm
Inner diameter (nominal)	280 + 40/-35 µm
Maximum pore size (calculated from BP)	≤ 0.2 µm
Bubble point (Isopropylalcohol, 23°C)	≥ 3.0 bar
Tensile strength	≥ 150 cN
Elongation at break	≥ 400 %
Explosion pressure	≥ 3.0 bar
Implosion pressure	≥ 3.5 bar

Membrane performance characteristics	
Nitrogen flux	75 ± 30 ml/[min x cm ² x bar]

Available make-up configurations	
Single-thread spools	

All specifications are based on 3M internal test procedures and represent average lot performance.

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

3M and Membrana are trademarks of 3M Company. © 2018 3M Company. All rights reserved.

3M
Separation and Purification
Sciences Division
13840 South Lakes Drive
Charlotte, North Carolina
28273 USA
Phone: +1 704 587 8888
Fax: +1 704 587 8610

3M Deutschland GmbH
Separation and Purification
Sciences Division
Öhder Straße 28
42289 Wuppertal Germany
Phone: +49 202 6099 - 0
Fax: +49 6099 - 241

MM-1045
Rev. 09/2018

www.3m.com/membrana